

## CONSTRUCTION SPECIFICATION

### NV-31. REINFORCED CONCRETE

#### PART I - FURNISHING CONCRETE

##### 1. SCOPE

The work shall consist of furnishing portland cement concrete as required on the construction drawings. All materials, test procedures, and admixtures shall meet the requirements of the latest edition of the applicable ASTM designation.

The mix proportion in this specification is required to yield a 28-day compressive strength of 3500 psi or more. If the required compressive strength shown on the drawings is greater than 3500 psi, the contractor shall provide a concrete mix design and laboratory testing that verifies the concrete supplied will produce compressive strengths which equal or exceed the strength required.

Failure to meet any requirements contained in this specification shall be cause for rejection of the concrete.

##### 2. MATERIALS

The contractor shall provide the Technician with test data, independent laboratory reports, or other evidence from the concrete supplier showing that all materials meet the requirements of this specification.

The use of any admixtures in the concrete mix shall be in strict compliance with the manufacturer's recommendations.

- A. Portland cement shall conform to ASTM C 150 and shall be Type IP(MS), II, IIA, or V.
- B. Fine aggregate shall conform to ASTM C 33 and be composed of clean, uncoated grains of material.
- C. Coarse aggregates shall be gravel or crushed stone conforming to ASTM C 33 and be clean, hard, durable, and free from clay or coating of any character. The maximum size coarse aggregate shall be 1-1/2 inches.
- D. Water shall be clean and free from injurious amounts of oil, salt, acid, alkali, organic matter, or other deleterious substances.
- E. Air entraining agent shall conform to ASTM C 260.
- F. Pozzolan (fly ash) shall be in strict compliance with ASTM C 618, Class F or C. The loss of ignition shall not exceed 6.0 percent.
- G. Ground Granulated Blast Furnace (GGBF) Slag shall conform to ASTM C 989.

H. Water-reducing admixtures shall conform to ASTM C 494 and may be the following types:

1. Type A - Water-reducing admixture.
2. Type D - Water-reducing and retarding admixture.
3. Type F - Water-reducing, high range admixture (superplasticizer).
4. Type G - Water-reducing, high range, and retarding admixture (superplasticizer).

Type D or G admixture may be used at the option of the contractor/supplier when the air temperature is over 80 degrees F at the time of mixing and/or placement.

I. Calcium chloride or other antifreeze compounds or accelerators will not be allowed.

### 3. DESIGN OF THE CONCRETE MIX

The air content (by volume) shall be 4 to 8 percent of the volume of the concrete at the time of placement.

The slump shall be 2 to 5 inches except when superplasticizer is used in the concrete mix. When superplasticizer is used, the slump shall be 3 inches or less prior to the addition of the admixture and shall not exceed 8 inches following addition and mixing. Additional superplasticizer shall not be added to the concrete mix after discharge of the concrete at the job site has commenced.

The fine aggregate oven dry weight shall be 30-45 percent of the total oven dry weight of the combined aggregates.

The following mix proportions per cubic yard may be used by the contractor/supplier to produce concrete with a minimum compressive strength of 3500 psi. Other mix proportions proposed by the contractor/supplier may be submitted to the Technician for approval prior to use.

<b>Mix Number</b>	<b>Minimum Cement Bags/Pounds</b>	<b>Fly Ash Pounds</b>	<b>GGBF** Slag Pounds</b>	<b>Maximum *** Water Gallons</b>
1*	6.0/564	0	0	36
2*	5.0/470	45-90	0	33
3*	4.25/400	0	165	32

\* Superplasticizer may be added to the mix.

\*\* Ground Granulated Blast Furnace

\*\*\* Total of aggregate moisture, mixing water added at the plant, and mixing water added at the job site.

### 4. MIXTURES AND MIXING

USDA-NRCS-Nevada  
Section IV, Technical Guide  
9/04

Ready-mixed concrete shall be batched, mixed and transported in accordance with ASTM C 94.

Concrete shall be uniform and thoroughly mixed when delivered to the forms.

No mixing water in excess of the amount shown for the design mix or in an amount that would cause the maximum slump to be exceeded shall be added to the concrete during mixing, hauling or after arrival at the delivery point.

The concrete shall be batched and mixed such that the temperature of the concrete at time of placing shall not be less than 50 degrees F nor more than 90 degrees F.

#### 5. BATCH TICKET INFORMATION

The contractor shall obtain from the supplier a delivery ticket for each batch of concrete before unloading at the site. The following minimum information shall be included on the ticket:

- A. Name of concrete supplier and batch plant.
- B. Name of purchaser and job location.
- C. Date of delivery.
- D. Truck number.
- E. Amount of concrete delivered.
- F. Time loaded or time of first mixing of cement and aggregates.
- G. Mixing water in the load added as free water.
- H. Type and amount of cement.
- I. Type and amount of admixtures.
- J. Oven dry weights of fine and coarse aggregate.
- K. Percent moisture content or weight of water contained in the aggregates.

The contractor or inspector shall also include the following additional information on the batch ticket:

- A. Water added by the receiver of the concrete.
- B. Time the concrete arrived at the site.
- C. Time the concrete was completely unloaded.

Upon completion of the concrete placement, copies of all load tickets shall be provided to the Technician.

Materials information that will remain constant throughout the job may be provided by the supplier and approved by the Technician prior to placing concrete. This materials information may be omitted from the load ticket.

## PART II - CONCRETE INSTALLATION

### 1. SCOPE

The work shall consist of forming, placing, finishing, and curing Portland cement concrete and the furnishing and placing of steel reinforcement as required on the construction drawings.

Failure to meet any requirements contained in this specification shall be cause for rejection of the concrete installed.

### 2. MATERIALS

Preformed expansion joint filler shall be commercially available products made of bituminous, sponge rubber or closed cell foam materials with a minimum thickness of 1/2 inch.

Reinforcing steel for concrete reinforcement shall meet the requirements of ASTM A 615. The steel shall be deformed Grade 40 or Grade 60 billet-steel bars unless otherwise noted on the plans.

Dowels shall be plain round bars conforming to the same specifications for reinforcing steel.

Waterstops shall be either metallic or nonmetallic. Metallic waterstops shall be fabricated from sheets of copper or galvanized steel having a minimum width of 8 inches. Nonmetallic waterstops shall be made of rubber (natural or synthetic) or vinyl chloride polymer or copolymer having a minimum width of 6 inches or as shown on an NRCS approved standard drawing and a minimum web thickness of 3/16 inches. Rubber, polymer and copolymer waterstops shall have ribbed or bulb-type anchor flanges and a hollow tubular center bulb. Other types of acceptable nonmetallic waterstops shall be as shown on the construction drawings.

Curing compound shall be a liquid membrane-forming compound suitable for spraying on the concrete surface. The curing compound shall meet the requirements of ASTM C 309 Type 2 (white pigmented).

### 3. DEFINITIONS

The following definitions are provided for the purpose of this specification.

*Firm* refers to subgrade not significantly displaced or deformed by foot traffic during construction and is able to properly support reinforcement chairs.

*Flatwork* refers to concrete poured on slopes flatter than 5:1 (Horizontal:Vertical).

*Sloped slabs* refers to concrete poured on slopes of 5:1 (Horizontal:Vertical) or steeper.

### 4. REINFORCING STEEL

USDA-NRCS-Nevada  
Section IV, Technical Guide  
9/04

Reinforcing steel shall be cut and bent according to ACI Standard 315.

Before reinforcement is placed, the surfaces of the bars shall be cleaned to remove any loose, flaky rust, mill scale, oil, grease, or other foreign substances. After placement, the reinforcement shall be maintained in a clean condition until it is completely embedded in the concrete.

Reinforcement shall be accurately placed as shown on the drawings and secured in position in a manner that will prevent its displacement during the placement of concrete. Metal chairs, metal hangers, metal spacers, or concrete chairs shall be used to support the reinforcement. Precast concrete chairs shall be manufactured from concrete equal in quality to the concrete being placed. Precast concrete chairs shall be moist at the time concrete is placed.

Reinforcement for *sloped slabs or flatwork* shall be supported by a minimum of 1 support chair every third bar or every 4 feet in each direction, whichever spacing is smaller. Support chairs shall have a minimum basal area of 4 square inches in contact with the subgrade.

Splices of reinforcing steel shall be made only at the locations shown on the drawings unless otherwise approved by the Technician.

## 5. PREPARATION OF FORMS AND SUBGRADE

The site shall be graded to the dimensions and elevations as specified in the construction plans.

Prior to placement of concrete, the forms and subgrade shall be free of woodchips, sawdust, debris, water, ice, snow, extraneous oil, mortar, or other harmful substances or coatings. Any oil on the reinforcing steel or other surfaces required to be bonded to the concrete shall be removed. Rock surfaces shall be cleaned by air-water cutting, wet sandblasting, or wire brush scrubbing as necessary.

All surfaces shall be firm and damp prior to placing concrete. Placement of concrete on mud, dried earth, uncompacted fill, or frozen subgrade will not be permitted. The use of plastic sheeting to isolate the concrete from unsuitable foundations will not be permitted.

The forms and associated false-work shall be substantial and unyielding and shall be constructed so that the finished concrete will conform to the specified dimensions and contours. Forms shall be mortar tight. Forms with torn surfaces, worn edges, dents or other defects will not be used. Forms shall be coated with a non-staining form release agent before being set into place. Excess form coating material shall not stand in puddles in the forms nor come in contact with the steel reinforcement or with hardened concrete against which fresh concrete is to be placed.

Form accessories to be partially or wholly embedded in the concrete, such as ties and hangers, shall be of a commercially manufactured type. Non-fabricated wire shall not be used. Form ties shall be constructed so that the ends or end fasteners can be removed without causing spalling at the surface of the concrete.

Steel tying and form construction adjacent to new concrete shall not be started until the concrete has cured at least 12 hours.

Concrete joints shall be of the type and at locations shown on the construction drawings.

Waterstops shall be located as shown on the drawings and secured in position so that displacement does not occur during concrete placement. Waterstops may be secured to reinforcement using wire or "hog ring" type fasteners.

Factory fabricated waterstop corners and transitions shall be provided, leaving only straight butt joint splices for field fabrication. Splices in waterstops shall be welded as recommended by the manufacturer.

**Subgrade and form preparation for *sloped slabs* shall meet the following additional requirements:**

- a. If the existing subgrade is not firm, it shall be made firm according to one of the following methods:
  - i. Compacted according to Nevada Construction Specification NV-23, Earthfill
  - ii. The addition of materials such as crushed rock, fines, or other amendments approved by the Technician. The surface must then be compacted sufficiently to achieve a firm surface.
- b. Subgrade with Unified Soil Classification of SP, SW, GP, or GW shall not be steeper than 2.5:1 (H:V).
- c. Steel shall be tied at every other rebar intersection or as approved by the Technician.
- d. Steel shall be anchored to prevent any movement down the slope.
- e. Joints with waterstop shall not be placed horizontally across *sloped slabs* except for small incidental areas.

**6. PLACING AND FINISHING CONCRETE**

**Concrete shall not be placed until the subgrade, forms, and steel reinforcement have been inspected and approved by the Technician.** Any deficiencies are to be corrected before the concrete is delivered for placement.

The contractor shall furnish the Technician a delivery ticket as specified in Part I for each load of concrete delivered to the site.

Concrete shall be delivered to the site and discharged into the forms within 1-1/2 hours after the introduction of the cement to the aggregates or when a superplasticizer is used, the manufacturer's recommended time limit for discharge after addition shall apply. In hot weather or under conditions contributing to quick stiffening of the concrete, discharge of the

concrete shall not exceed 45 minutes unless a set-retarding admixture is used or the mix is remaining workable.

Upon arrival at the job site, addition of water will be allowed to adjust the slump, provided such addition does not exceed the specified limits of the slump or maximum water content contained in the design mix. A small amount of concrete may be discharged prior to the addition of water. Final placement of the batch shall begin immediately after mixing of the added water is completed. No additional water shall be added to the mix after placement has begun.

Concrete shall be deposited as closely as possible to its final position in the forms and shall be worked into the corners and angles of the forms and around all reinforcement and embedded items in a manner to prevent segregation of aggregates. Placement of concrete for *sloped slabs* may also be achieved by gravity flow. All placement shall be done in a manner that prevents incorporation of subgrade material into the concrete.

The Technician shall obtain adequate documentation of the constructed slab thickness to ensure concrete placement as shown in the construction plan.

If the concrete sets during placement to the degree that it will not flow and merge with the succeeding pour when tamped or vibrated, the contractor shall discontinue placing concrete and install a formed construction joint. The contractor shall be prepared to install unplanned construction joints in the event that there is an interruption of the pour, equipment breakdown, or other problem which makes it necessary to stop placement of concrete other than those previously planned. Prior to commencement of concreting operations at the construction joint, the joint surface shall be cleaned to remove all laitance, exposed sand, and surface mortar by one of the following methods:

- a. The joint surface shall be cleaned to expose coarse aggregate by sandblasting or air-water cutting after the concrete has gained sufficient strength to prevent displacement of the coarse aggregate or cement fines. The surface of the concrete shall not be cut so deep as to undercut the coarse aggregate. The joint surface shall be washed to remove all loose material after cutting.
- b. According to methods specified by the construction plan approver.

The surfaces of all construction joints shall be wetted and standing water removed immediately prior to placement of the new concrete. The new concrete shall be placed directly on the cleaned and washed surface. New concrete shall not be placed until the hardened concrete has cured at least 12 hours. The newly placed concrete shall be consolidated to achieve a good bond with the previously hardened concrete.

Concrete mixes not containing superplasticizer shall not be dropped more than 5 feet vertically unless suitable equipment is used to prevent segregation. Concrete mixes containing superplasticizer shall not be dropped more than 12 feet vertically and shall be placed in lifts not exceeding 5 feet in depth.

Immediately after the concrete is placed in the forms, it shall be consolidated by vibration or hand tamping as necessary to insure dense concrete. Walls four (4) feet and higher shall

be vibrated. Concrete supplied with superplasticizer shall be placed with a minimum amount of vibrating and finishing effort. Vibration shall not be applied directly to the reinforcement steel or the forms nor to concrete that has hardened to the degree that it does not become plastic when vibrated. Each pour shall be consolidated to insure a monolithic bond with the preceding pour. The use of vibrators to transport concrete in the forms, slabs or conveying equipment will not be permitted.

Vibration is required at all joints that contain waterstop.

*All flatwork* shall be screeded to grade and then bull-floated. Vibratory screeding may be used in lieu of bull-floating. An additional finish may be specified. All flatwork surfaces shall be true and even, and shall be free from open or rough spaces, depressions, or projections.

*Sloped slabs* shall be worked to a uniform grade, maintaining the specified thickness, and finished in a manner to insure dense concrete. All sloped slab surfaces shall be smooth, and shall be free from open or rough spaces, depressions, or projections.

## 7. FORM REMOVAL AND FINISHING

Forms shall be removed in such a way as to prevent damage to the concrete. Supports shall be removed in a manner that will permit the concrete to take the stresses due to its own weight uniformly and gradually. Wall forms and forms for joints with waterstop shall not be removed for 24 hours after the concrete is placed except in the case of tank covers which require the forms to remain in place for 7 days. Other forms may be removed when the concrete is sufficiently cured so that the concrete will not be damaged.

Immediately after removal of the forms, concrete which is honey combed, damaged or otherwise defective shall be repaired or replaced as directed by the Technician. Repairs are to be made in accordance with American Concrete Institute (ACI) 301, Specifications for Structural Concrete. The procedure is contained in the section for repair of surface defects other than tie holes. All repaired areas shall be cured as specified in Section 7.

For structures which are not required to be liquid-tight, form ties shall be removed flush with or below the concrete surface.

For structures which are to be liquid-tight, form ties shall be removed to a minimum depth of 1/2 inch. All cavities or depressions resulting from form tie removal shall be patched with commercially available patching products including:

- Portland cement mortar modified with a latex bonding agent conforming to ASTM C 1059, Type 11.
- Epoxy mortars and epoxy compounds that are moisture-insensitive during application and after curing and that embody an epoxy binder conforming to ASTM C 881, Type 111.
- Non-shrink Portland cement grout conforming to ASTM C 1107.
- Packaged dry concrete repair materials conforming to ASTM C 928.

The age of stripped concrete or slabs shall be at least 7 days before any load (including backfill) is applied other than the weight of the wall, forms, scaffolds for succeeding lifts or light equipment.

#### 8. CURING

Concrete shall be cured for a period of at least 7 days after it is placed. Exposed surfaces shall be kept continually wet during the entire curing period or until curing compound is applied.

Curing compound shall be applied at the rate recommended by the manufacturer, as a minimum. It shall form a uniform, continuous, adherent film that shall not check, crack, or peel and shall be free from pinholes or other imperfections.

Curing compound shall not be used at construction joints or other areas that are to be bonded to additional concrete. These areas shall be wet cured. Surfaces subjected to heavy rainfall or running water within 3 hours after the application of curing compound, or surfaces damaged by subsequent construction operations during the curing period, shall be recoated in the same manner as the original application.

#### 9. CONCRETING IN HOT WEATHER

For the purpose of this specification, hot weather is defined as any combination of high temperature, (generally above 80 degrees F), low relative humidity, and wind velocity tending to impair the quality of fresh or hardened concrete or otherwise resulting in abnormal properties.

Special provisions shall be made to immediately protect and cure the concrete due to rapid drying conditions. Concrete surfaces shall not be allowed to dry after placement and during the curing period. Wood form surfaces shall be kept continuously moist.

In extreme conditions, it may be necessary to (1) restrict placement to late afternoon or evening, (2) restrict the depth of layers to assure coverage of the previous layer while it will still respond readily to vibration, (3) suspend placement until conditions improve.

#### 10. CONCRETING IN COLD WEATHER

When the minimum daily atmospheric temperature is less than 40 degrees F, concrete shall be insulated or housed and heated immediately after placement. The temperature of the concrete and air adjacent to the concrete shall be maintained at not less than 50 degrees F no more than 90 degrees F for the duration of the curing period.

Combustion heaters shall have exhaust flue gases vented out of the concrete protection enclosure and shall not be permitted to dry the concrete.

The contractor shall furnish the Technician a record of daily maximum and minimum outside air and concrete surface air temperatures during the curing period. The record shall include temperatures at several points along the concrete.

## 11. BASIS OF ACCEPTANCE

The acceptability of the reinforced concrete shall be determined by inspection to check compliance with all the provisions of this specification, with respect to the drawings, and the minimum installation requirements.

Materials used shall be certified as meeting the requirements of this specification. The installing Contractor shall certify that the installation complies with the requirements of this specification. A written guarantee shall be furnished that protects the Owner against defective workmanship and materials for no less than one year.